



**Florida
Test**



**Total duration:
12 months**



From **15/07/2013** to **17/07/2014**



**Florida
Test**



**Total duration:
36 months**



From **15/07/2013** to **15/07/2016**

**Unexposed
area
(reference)**

**Exposed
area**



**Unexposed
area
(reference)**

**Exposed
area**



LAB. ID NUMBER: 30861
POWDER COATING: DS-0742S
HEAT TRANSFER FILM: 82531/01 L4
Colour variation (ΔE): **0,49**
residual gloss: **100%**

**Approved
combination:**



LAB. ID NUMBER: 31218
POWDER COATING: DS-0742S
HEAT TRANSFER FILM: 82531/01 L4
Colour variation (ΔE): **2,13**
residual gloss: **63%**

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).