



Florida
Test



Total duration:
12 months



Florida
Test



Total duration:
36 months



From 15/07/2013 to 17/07/2014



From 15/07/2013 to 15/07/2016

Unexposed
area
(reference)

Exposed
area



Unexposed
area
(reference)

Exposed
area



LAB. ID NUMBER: 30862
POWDER COATING: DS-0742S
HEAT TRANSFER FILM: 82602/02 L4
Colour variation (ΔE): 0,54
residual gloss: 100%

Approved
combination:



LAB. ID NUMBER: 31219
POWDER COATING: DS-0742S
HEAT TRANSFER FILM: 82602/02 L4
Colour variation (ΔE): 2,15
residual gloss: 64%

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).