



Florida  
Test



Total duration:  
12 months



Florida  
Test



Total duration:  
36 months



From 15/07/2013 to 17/07/2014



From 15/07/2013 to 15/07/2016

Unexposed  
area  
(reference)

Exposed  
area



Unexposed  
area  
(reference)

Exposed  
area



LAB. ID NUMBER: 30876  
POWDER COATING: DS-0772S  
HEAT TRANSFER FILM: 82308/17 L4  
Colour variation ( $\Delta E$ ): 0,88  
residual gloss: 100%

Approved  
combination:



LAB. ID NUMBER: 31233  
POWDER COATING: DS-0772S  
HEAT TRANSFER FILM: 82308/17 L4  
Colour variation ( $\Delta E$ ): 1,91  
residual gloss: 56%

**QUALICOAT REQUIREMENTS**

The residual value shall be at least 75% of the original gloss.  
The  $\Delta E$  values not greater than 65% of the limits in the table  
(see Appendix A7 of Qualicoat Specifications).

**QUALICOAT REQUIREMENTS**

The residual value shall be at least 50% of the original gloss.  
The  $\Delta E$  values within the limits prescribed in the annexed  
table (see Appendix A7 of Qualicoat Specifications).