



**Florida  
Test**



**Total duration:  
60 months**



**EXPOSURE PERIOD:**

**FROM: 01/06/2014**

**TO: 21/07/2019**

LAB. ID NUMBER: 47432  
POWDER COATING: MirrorL-183S25  
HEAT TRANSFER FILM: 86053/01 L4  
colour variation ( $\Delta E$ ): 1,98  
residual gloss: 83%

### Technical Remarks

After 5 years of exposure in Florida, the sample has a good residual gloss and normal colour variation, the aspect still remains good.



Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

The final evaluation will be based on visual inspection with the naked eye and using grey scale (ISO 105-A02).

