



**Florida  
Test**



**Total duration:  
60 months**



**EXPOSURE PERIOD:**

**FROM: 01/06/2014**

**TO: 21/07/2019**

LAB. ID NUMBER: 47438  
POWDER COATING: 17C-945-A001  
HEAT TRANSFER FILM: 82602/04 L8  
colour variation ( $\Delta E$ ): 2,50  
residual gloss: 68%

### Technical Remarks

After 5 years of exposure in Florida, the sample has a sufficient residual gloss and high colour variation, the aspect still remains good.



Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

The final evaluation will be based on visual inspection with the naked eye and using grey scale (ISO 105-A02).

**Unexposed area  
(reference)**

**Exposed  
area**

