





Deep Matt 2.0


Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		134	
Laboratory Test	No. 708	Device: QSun 3000H	Total duration: 1152 h		
					
LAB. ID NUMBER: 57457 POWDER COATING: Deep Matt-001 HEAT TRANSFER FILM: 2501/05 colour variation (ΔE): 1,73 residual gloss: 85%					
Technical Remarks Good residual gloss and normal variation (ΔE), after 1152 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 13/10/2025 ID Report: TR-IA-134-2025					

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		133	
Laboratory Test	No. 708	Device: QSun 3000H	Total duration: 1152 h		
					
LAB. ID NUMBER: 57455 POWDER COATING: Deep Matt-002 HEAT TRANSFER FILM: 2512/02 colour variation (ΔE): 1,78 residual gloss: 96%					
Technical Remarks Excellent residual gloss and normal variation (ΔE), after 1152 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 13/10/2025 ID Report: TR-IA-133-2025					

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		130	
Laboratory Test	No. 708	Device: QSun 3000H	Total duration: 1152 h		
					
LAB. ID NUMBER: 57452 POWDER COATING: Deep Matt-007 HEAT TRANSFER FILM: 2308/24 colour variation (ΔE): 2,19 residual gloss: 81%					
Technical Remarks Excellent residual gloss and normal variation (ΔE), after 1152 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 13/10/2025 ID Report: TR-IA-130-2025					

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		128	
Laboratory Test	No. 708	Device: QSun 3000H	Total duration: 1152 h		
					
LAB. ID NUMBER: 57440 POWDER COATING: Deep Matt-007 HEAT TRANSFER FILM: 2002/06 colour variation (ΔE): 2,02 residual gloss: 89%					
Technical Remarks Excellent residual gloss and normal variation (ΔE), after 1152 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 13/10/2025 ID Report: TR-IA-128-2025					

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		127	
Laboratory Test	No. 708	Device: QSun 3000H	Total duration: 1152 h		
					
LAB. ID NUMBER: 57448 POWDER COATING: Deep Matt-003 HEAT TRANSFER FILM: 6047/04 colour variation (ΔE): 0,64 residual gloss: 91%					
Technical Remarks Excellent residual gloss and low variation (ΔE), after 1152 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 13/10/2025 ID Report: TR-IA-127-2025					

Test Report: Accelerated Weathering Test		Decoral LAB Research and Development		125	
Laboratory Test	No. 708	Device: QSun 3000H	Total duration: 1152 h		
					
LAB. ID NUMBER: 57446 POWDER COATING: Deep Matt-003 HEAT TRANSFER FILM: 6026/04 colour variation (ΔE): 1,01 residual gloss: 96%					
Technical Remarks Excellent residual gloss and low variation (ΔE), after 1152 hours.				Technical Opinion: Suitable for OUTDOOR USE	
Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.					
Mod_TR_01_rev03 Laboratory Decoral System Date: 13/10/2025 ID Report: TR-IA-125-2025					

Suitability for outdoor use of different combinations between polyurethane Decorall System® Powder Coatings and heat transfer film Decorall System® must be assessed on www.decorall-system.com. (link: **TESTED FOR OUTDOOR USE**) or contacting our laboratory.


Deep Matt 2.0

L'ideoneità all'impiego in esterno degli abbinamenti tra prodotti vernicianti poliuretanici Decorall System® e film sublimatici Decorall System® dovrà essere valutata sul sito internet www.decorall-system.com (alla voce **FINITURE ADATTE PER USO ESTERNO**) oppure contattando il nostro laboratorio.

MRK-005-1170



Powder Coating: Deep Matt-003 + Heat Transfer Film: 5026/04



Powder Coating: Deep Matt-003 + Heat Transfer Film: 6047/04




Powder Coating: Deep Matt-007 + Heat Transfer Film: 2602/08



Powder Coating: Deep Matt-007 + Heat Transfer Film: 2308/24



Powder Coating: Deep Matt-002 + Heat Transfer Film: 2512/02



Powder Coating: Deep Matt-001 + Heat Transfer Film: 2501/05